


材料 / Material: TN150P

特点 / Features:

1. 高磁导率 / High Initial Permeability



Initial permeability	μ_i	25°C	1500±20%
Saturation magnetic flux density	Bs(mT) 1600A/m	25°C	300
Relative loss factor 100kHz	$\tan\delta/\mu_i$ ($\times 10^{-6}$)	25°C	≤20
Relative temperature coefficient	$\alpha_{\mu r}$ ($\times 10^{-6}/^{\circ}\text{C}$)	20 ~ 60°C	5
Curie temperature	Tc(°C)		>110
Electrical resistivity	$\rho(\Omega\cdot\text{m})$		10^6
Density	d(kg/m ³)		5.2×10^3

Test core : Toroid(mm)

OD : 12.7

ID : 7.9

H : 6.5

